

Prime Floors

Homogeneous Flooring Tiles

Test Item	Standards Requirements	Unit	Test Result
Size	303 X 303	mm	303 X 303
Thickness	2	mm	1.93
Package	4.59	m ² /CTN	-
Weight	4.3	KG/m ²	4.1
Angle Deviation	≤0.25	mm	0.08
Length change rate after-heating	≤ 0.2	%	0.07
Length change rate after-absorbing water	≤ 0.2	%	0.07
Rudimental Dent	$0.15 < I_r \leq 0.4$	mm	0.18
Fire Resistance	B1 (B-S1, TO)CLS	-	B1 (B-S1, TO) CLS

Prime Floors

Homogeneous Flooring Tiles




Prime Floors

Homogeneous Flooring Tiles

Prime Floors

Homogeneous Flooring Tiles



2.0 mm X 303 mm X 303 mm 50 pcs / case = 4.59 m²/case



TCD 308




TCD 310



TCD 311



TCD 317



TCD 318



TCD 324



TCD 316




TCD 328




TCD 315

Prime Floors

Homogeneous Flooring Tiles



2.0 mm X 303 mm X 303 mm 50 pcs / case = 4.59 m²/case



TCD 325



TCD 323



TCD 326



TCD 303



TCD 306



TCD 320